Vacuum Conditioning

Motors are supplied pre-baked to 200 °C in 1 x 10^{-6} mbar pressure for 24 hours and vented with dry Nitrogen before vacuum packaging. They may still adsorb water in storage and handling so a 24-hour bake by an AML stepper motor drive, with an adequate pump is recommended to achieve UHV-compatibility.